

38M1040AA0606(000000000)



Part Number: 38M1040AA0606

Material Grade	M1
Sheet Size	60 x 60 mm
Ferrite Thickness	0.4 mm
Total Thickness	0.43 mm

nominal inch



Dim

Weight: (g)

Chart Legend

mm mm tol

A	_						
Typical Shielding Effectiveness (dB): Test Method as noted -> **, ***							oted -> **,
PART	NUMBER	Material	1MHz**	6.78MHz**	13.56MHz**	100MHz***	300MHz***
38M1	04044060	6 M1	4.7	4.7	4.7	5 1	5

inch misc.

** Shielding Effectiveness (SE) at 1 -50MHz:
measured using IEC
6233-2 Rde Inter
Decoupling Ratio method (loop to loop distance=
6mm).

This method is meaningful as a measure of decoupling effectiveness circuit to circuit or to metal surfaces (plane to plane).


*** Shielding
Effectiveness (SE) at
100MHz+: measured
using IEC 6233-2 Rrs
Radiation Suppression
Ratio method (50-ohm
Microstripline).


This method is meaningful as a measure of shielding for radiated emissions of "antennas".


Equipment Used:

E5072A Vector Network Analyzer (30kHz - 8.5 GHz) HP4291A RF Impedance/Material Analyzer (1MHz-3GHz) E4991A with 16453A Dielectric Test Fixture HP4284A for Temperature testing 25mm diameter slotted loop antennas 50-ohm Micro-Stripline Test Fixture

dB IEC 62333-2 (Rrs at 10mm) Comparison of Flex Materials: 60x60x0.5 mm size







Fair-Rite Products Corp. • One Commercial Row, Wallkill, New York 12589-0288

888-324-7748 • 845-895-2055 • Fax: 845-895-2629 • ferrites@fair-rite.com • www.fair-rite.com