

EMI Suppression Beads (2673001601)



Part Number: 2673001601

73 SHIELD BEAD

Explanation of Part Numbers:

- Digits 1 & 2 = Product Class
- Digits 3 & 4 = Material Grade
- Last digit 1= Not Burnished 2 = Burnished
- The last digit of the Parylene coated part is a "4," which is available upon request. The minimum coating thickness beads is 0.005 mm (0.0002).

Fair-Rite offers a broad selection of ferrite EMI suppression beads with guaranteed minimum impedance specifications.

Our "Shield Bead Kit" (part number 0199000019) contains a selection of these beads.

For any EMI suppression bead requirement not listed here, feel free to contact our customer service for availability and pricing.

Catalog Drawing 3D Model

The C dimension, the bead length, can be modified to suit specific applications.

Weight: 0.11 (g)

A 3.55 ±0.15 0.14 _ B 1.65 +0.25 0.07	Dim	mm	mm tol	nominal inch	inch misc.	75 (=5	
	A	3.55	±0.15	0.14	_		
0 0 0 0 0 0 100	В	1.65	+0.25	0.07	_		
C 3.3 -0.40 0.122 _	С	3.3	-0.40	0.122	_		






Chart Legend

- + Test frequency
- The column "H (Oe)" gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of "H" times the actual

NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note ☐How to choose Ferrite Components for EMI Suppression☐.


Typical Impedance (Ω					
1 MHz	7.2				
5 MHz	16				
10 MHz ⁺	22.5				
25 MHz ⁺	26				
Electrical Properties					
H(Oe)	1.6				

Suppression beads are controlled for impedances only. Minimum impedance values are specified for the + marked frequencies. The minimum impedance is typically the listed impedance less 20%.

Catalog Drawing

Single turn impedance tests for 73 and 43 material beads are performed on the E4990A Impedance Analyzer. The 61 material beads are tested on the E4991A / HP4291B Impedance Analyzer. Beads are tested with the shortest practical wire length.

Typical Impen	dance (Ω)
1 MHz	5.1
5 MHz	12.5
10 MHz ⁺	16
25 MHz ⁺	24



CSV Download

Fair-Rite Products Corp. • One Commercial Row, Wallkill, New York 12589-0288 888-324-7748 • 845-895-2055 • Fax: 845-895-2629 • ferrites@fair-rite.com • www.fair-rite.com